

In re Application of: Aharon J. AGRANAT et al
Serial No.: 10/566,264
Filed: April 17, 2007
Office Action Mailing Date: February 26, 2010

Examiner: CHANG Audrey Y.
Group Art Unit: 2872
Attorney Docket: 31316
Confirmation No.: 3491

In the Claims:

1. (Withdrawn and Currently Amended) An electroholographic switch, having:

an electro-optic crystal, in which an electrically controlled Bragg grating is stored by the method of claim 24, said electrically controlled Bragg grating being operable to deflect an incoming beam, which meets Bragg's condition for said grating, when an external electric field is applied to said crystal; and

a power supply, for providing said external electric field,

the improvement comprising permanently storing said electrically-controlled Bragg grating in said electro-optic crystal as periodic striations, produced as a concentration grating, during a growth process of said electro-optic crystal.

2. (Withdrawn) The electroholographic switch of claim 1, and further including a component of Bragg grating, operable in the absence of an electric field.

3. (Withdrawn) The electroholographic switch of claim 1, operable at a temperature range of between about 10 and about 80 degrees centigrade.

4. (Withdrawn) The electroholographic switch of claim 1, capable of withstanding storage temperature as high as 300 degrees centigrade.

5. (Withdrawn) The electroholographic switch of claim 1, and further including a temperature-control device, for maintaining said electro-optic crystal at a predetermined temperature.

In re Application of: Aharon J. AGRANAT et al
Serial No.: 10/566,264
Filed: April 17, 2007
Office Action Mailing Date: February 26, 2010

Examiner: CHANG Audrey Y.
Group Art Unit: 2872
Attorney Docket: 31316
Confirmation No.: 3491

6. (Withdrawn) The electroholographic switch of claim 5, wherein said predetermined temperature is within ± 3 degrees centigrade of a curie temperature of said electro-optic crystal.

7. (Withdrawn) The electroholographic switch of claim 5, wherein said predetermined temperature is between about 1 and about 5 degrees centigrade above of a curie temperature of said electro-optic crystal.

8. (Withdrawn) The electroholographic switch of claim 5, wherein said predetermined temperature is above of the Curie temperature of said electro-optic crystal.

9. (Withdrawn) The electroholographic switch of claim 1, wherein said concentration grating creates a grating in the phase transition temperature, T_c , which at the paraelectric phase, yields a grating in the dielectric constant.

10. (Withdrawn) The electroholographic switch of claim 9, wherein said grating in the phase transition temperature, T_c , has an amplitude of between about 0.1 degrees and about 2 degrees K.

11. (Withdrawn) The switch of claim 1, wherein said concentration grating has a period spacing of between about 0.1 and about 20 μm .

12. (Withdrawn) The electroholographic switch of claim 1, wherein said electro-optic crystal is KTN, and said concentration grating is formed by changes in concentration between niobium and tantalum.

In re Application of: Aharon J. AGRANAT et al
Serial No.: 10/566,264
Filed: April 17, 2007
Office Action Mailing Date: February 26, 2010

Examiner: CHANG Audrey Y.
Group Art Unit: 2872
Attorney Docket: 31316
Confirmation No.: 3491

13. (Withdrawn) The electroholographic switch of claim 1, wherein said electro-optic crystal is KLTN, and said concentration grating is formed by changes in concentration between niobium and tantalum.

14. (Withdrawn) The electroholographic switch of claim 1, wherein said electro-optic crystal is KLTN, and said concentration grating is formed by changes in concentration between lithium and potassium.

15. (Withdrawn) The electroholographic switch of claim 1, wherein said electro-optic crystal is KLTN, and said concentration grating is formed by changes in concentrations of niobium, lithium, and potassium.

16. (Withdrawn) The electroholographic switch of claim 1, wherein said electro-optic crystal is KNTN, and said concentration grating is formed by changes in concentration between sodium and potassium.

17. (Withdrawn) The electroholographic switch of claim 1, wherein said electro-optic crystal is KNTN, and said concentration grating is formed by changes in concentration between niobium and potassium.

18. (Withdrawn) The electroholographic switch of claim 1, wherein said electro-optic crystal is KNTN, and said concentration grating is formed by changes in concentrations of niobium, sodium, and potassium.

19. (Withdrawn) The electroholographic switch of claim 1, wherein said electro-optic crystal is selected from the group consisting of SBN and BST.

20. (Withdrawn) The electroholographic switch of claim 1, wherein said external electric field is 0 and 5kV/cm.

In re Application of: Aharon J. AGRANAT et al
 Serial No.: 10/566,264
 Filed: April 17, 2007
 Office Action Mailing Date: February 26, 2010

Examiner: CHANG Audrey Y.
 Group Art Unit: 2872
 Attorney Docket: 31316
 Confirmation No.: 3491

21. (Withdrawn) The electroholographic switch of claim 1, selected from the group consisting of a wavelength selection switch and a switch for different angles of incidence.

22. (Withdrawn and Currently Amended) An electroholographic switch, having:

an electro-optic crystal, in which a Bragg grating is stored as periodic striations by the method of claim 24, ~~produced as a concentration grating during the growth process of said electro-optic crystal~~; and

a power supply, in communication with said crystal, for providing an external electric field, to selectively detune said Bragg grating.

23. (Withdrawn) An electroholographic switch, having:

an electro-optic crystal, in which a Bragg grating is stored as periodic striations, produced as a concentration grating during the crystal-growth process of said electro-optic crystal; and

a power supply, in communication with said crystal, for providing an external electric field, to selectively tune said Bragg grating.

24. (Currently Amended) A method of permanently storing spatial periodicity in phase-transition temperature ~~an electrically controlled Bragg grating into~~ an electro-optic crystal, comprising:

~~determining a birefringence grating, for a particular application;~~

~~determining~~ selecting periodic spatial modulation of ion concentration to be formed in the crystal, thereby determining a concentration grating to be formed in said crystal, wherein said selection is such that at said spatial modulation effects spatial periodicity in a phase-transition temperature within said crystal ~~which will yield said birefringence grating;~~

In re Application of: Aharon J. AGRANAT et al
 Serial No.: 10/566,264
 Filed: April 17, 2007
 Office Action Mailing Date: February 26, 2010

Examiner: CHANG Audrey Y.
 Group Art Unit: 2872
 Attorney Docket: 31316
 Confirmation No.: 3491

seeding a crystal seed in a solution; and
causing temporal periodic modulation in a temperature of said seed in said
solution so as to growing said electro-optic crystal on said seed at a said periodically
modulated~~ion in the growth~~ temperature, and to produce said concentration grating.

25. (Original) The method of claim 24, and further including growing said electro-optic crystal at a cooling rate of between about -0.1 and about -1.0 degrees centigrade per hour.

26. (Original) The method of claim 25, wherein said periodic modulation in the growth temperature is produced by a periodic modulation of said cooling rate.

27. (Original) The method of claim 24, and further including growing said electro-optic crystal at a pulling rate of between about 0.1 and about 1.5 mm per hour.

28. (Original) The method of claim 27, wherein said periodic modulation in the growth temperature is produced by a periodic modulation of said pulling rate.

29. (Canceled)

30. (Currently Amended) The method of claim 24, wherein said periodic modulation in the growth temperature is effected~~produced~~ by stirring said a growth solution.

31. (Original) The method of claim 30, and further including cyclically changing the direction of said stirring.

In re Application of: Aharon J. AGRANAT et al
Serial No.: 10/566,264
Filed: April 17, 2007
Office Action Mailing Date: February 26, 2010

Examiner: CHANG Audrey Y.
Group Art Unit: 2872
Attorney Docket: 31316
Confirmation No.: 3491

32. (Currently Amended) The method of claim 24, wherein said solution is heated in a crucible and wherein said periodic modulation in the growth temperature is effected ~~produced~~ by rotating said a growth crucible, when at a center position.

33. (Original) The method of claim 32, and further including cyclically changing the direction of said rotating.

34. (Currently Amended) The method of claim 24, wherein said solution is heated in a crucible and wherein said periodic modulation in the growth temperature is effected ~~produced~~ by rotating said a growth crucible, when at an off-center position.

35. (Currently Amended) The method of claim 24, wherein said periodic modulation in the growth temperature is produced by rotating said crystal or said seed during growth, when at a center position.

36. (Original) The method of claim 35, and further including cyclically changing the direction of said rotating.

37. (Currently Amended) The method of claim 24, wherein said periodic modulation in the growth temperature is produced by rotating said electro-optic crystal or said seed during growth, when at an off-center position.

38. (Original) The method of claim 24, wherein said periodic modulation in the growth temperature is varied between every 10 and every 30 seconds.

In re Application of: Aharon J. AGRANAT et al
 Serial No.: 10/566,264
 Filed: April 17, 2007
 Office Action Mailing Date: February 26, 2010

Examiner: CHANG Audrey Y.
 Group Art Unit: 2872
 Attorney Docket: 31316
 Confirmation No.: 3491

39. (Original) The method of claim 24, wherein said periodic modulation in the growth temperature is varied between every 10 and every 300 seconds.

40. (Original) The method of claim 24, wherein said periodic modulation in the growth temperature further including a pause of between 1 and 15 seconds between modulation cycles.

41. (Currently Amended) A method of growing a permanently storing an electrically controlled Bragg grating in an electro-optic crystal, comprising:
selecting determining a characteristic ion concentration periodic pattern, for a particular application;
seeding a crystal seed in a solution; and
causing temporal periodic modulation in a temperature of said seed in said solution so as to growing said electro-optic crystal on said seed at said a periodically modulated ion in the growth temperature, and to produce said characteristic ion concentration periodic pattern in said crystal.